

Product Description

Dymeric® 240FC is a gun-grade, multi-component, chemically-curing, polyurethane sealant that includes a tintable base, curative packet, and a choice of 70 standard colors. A Limestone Pretinted version is also available.

Basic Uses

Dymeric 240FC's applications range from pre-cast tilt-up concrete, masonry, and exterior insulating and finishing systems (EIFS), to metal curtain walls, and perimeter joints around doors and windows. It can also be used in certain water immersed applications.

Features and Benefits

- Dymeric 240FC is an all-around general-purpose sealant that provides flexible, long life and durable waterproofing for both new construction and restoration projects in a fast curing formulation.
- Dymeric 240FC is formulated to be a lightweight material designed for extremely easy mixing, even in cold temperatures.
- Dymeric 240FC is a solvent-free product that is compliant with all existing VOC regulations. Please contact your local Sales Representative or Tremco's Technical Service Department for information regarding immersed conditions.

Coverage Rates

308 linear feet of joint per gallon for a 1/4" X 1/4" joint. For specific coverage rates that include joint size, and usage efficiencies, visit our website usage calculator at www.tremcosealants.com.

Packaging

1.5-gal (5.7-L) and 3-gal (11.4-L) kits with pre-measured pouches of curing agent.

Colors

Dymeric 240FC is available as a base and curative that can be tinted to your choice of 70 standard colors, or we can match a special color for you. A color pak is not required for the pretint version.

Availability

Immediately available from your local Tremco Field Representative, Tremco Distributor or Tremco Warehouse.

Storage

Store Dymeric 240FC in original, undamaged packaging in a clean, dry, protected location with temperatures between 40 to 110 °F (5 to 43 °C).

Applicable Standards

Dymeric 240FC meets or exceeds the requirements of the following specifications:

- ASTM C920-02 Type M, Grade NS, Class 50, Use T, NT, M, A and O (granite), I (Class 2)
- U.S. Federal Specification TT-S-00227E Class A, Type II
- CAN/CGSB 19.24-M90 Class B, Type II
- UL 2079 (ASTM E1966), CAN/ULC S115

Fire Rated Systems

CJ-D-0015, CJ-D-0016, CJ-D-0017, FF-D-1061, FF-D-1181, FF-S-1030, FF-S-1046, FW-D-1057, FW-D-1112, FW-S-1024, FW-S-1014, HW-D-1052, HW-D-1119, HW-S-1011, WW-D-1052, WW-D-1197, WW-S-1033

Limitations

- Pot life (after curative packet added): 3.0 to 3.5 hr at 77 °F (25 °C), 1.5 to 2.0 hr at 95 °F (35 °C), 1.0 to 1.5 hr at 120 °F (48.9 °C).

- Do not apply Dymeric 240FC to damp or contaminated surfaces.
- Always utilize the accompanying MSDS for information on Personal Protective Equipment (PPE) and Health Hazards.
- The use of a Tremco Universal Color Pak is always required except with the pretinted Limestone.

Substrate Preparation

Surfaces must be sound, clean, and dry. All release agents, existing waterproofing, dust, loose mortar, laitance, paints, or other finishes or field applied coating must be removed. This can be accomplished with a thorough wire brushing, grinding, sandblasting, or solvent washing, depending on the contamination.

Tremco recommends that surface temperatures be 40 °F (5 °C) or above at the time the sealant is applied. If sealant must be applied in temperatures below 40 °F, please refer to the Tremco Guide for Applying Sealants in Cold Weather that can be found on our website at www.tremcosealants.com

Priming

Dymeric 240FC typically adheres to common construction substrates without primers; however, Tremco always recommends that mock-up or field adhesion test be performed on the actual materials being used on the job to verify the need for a primer, proper cleaning and prep requirements. The field adhesion test can be found in appendix X1 of ASTM C1193, Standard Guide for Use of Joint Sealants.

Where deemed necessary, use Tremco Primer #191 QD for porous substrates and TREMPprime Non-Porous Primer for metals and plastics.

Application

Mix in accordance with instructions on the pail using the entire pre-measured curative packet and your selected Universal Color Pak. One color pack should be used with 1.5-gal pails and 2 color packs should be used in the 3-gal pail. Mix all three parts for a minimum of 6 min, scraping the sides of the pail and until there are no color striations. A color pak is not required for the pretint version.

Ensure the backer rod is properly friction-fitted and any primers have been applied.

Apply sealant with conventional caulking equipment filling the joint from the backer rod up. Immediately tool the sealant with a spatula to ensure intimate contact with the joint walls.

Dry tooling is always preferred, although xylene can be used in limited amounts to slick the spatula if needed.

For a cleaner finish, mask the sides of the joint with tape prior to filling.

Joint Design

Dymeric 240FC may be used in any vertical or horizontal joint designed in accordance with accepted architectural/engineering practices. Joint width should be 4 times anticipated movement, but not less than 1/4" (6.4 mm).

Joint Backing


Closed cell or reticulated polyethylene backer rod is recommended as joint backing to control sealant depth and to ensure intimate contact of sealant with joint walls when tooling. Where depth of joint will prevent the use of backer rod, an adhesive backed polyethylene tape (bond breaker tape) should be used to prevent three-sided adhesion. All backing should be dry at time of sealant application.

Dymeric® 240FC

Fast-Curing, Multi-Component, Polyurethane Sealant

Sealant Dimensions

W = Sealant width, D = Sealant depth, C = Contact area.



EXPANSION JOINTS - The minimum width and depth of any sealant application should be 1/4" by 1/4" (6 mm by 6 mm). The depth (D) of sealant may be equal to the width (W) of joints that are less than 1/2" wide.

For joints ranging from 1/2" to 1" (13 mm to 25 mm) wide, the sealant depth should be approximately one-half of the joint width. The maximum depth (D) of any sealant application should be 1/2" (13 mm). For joints that are wider than 1" (25 mm) contact Tremco's Technical Service Department, or your local Tremco field representative.

WINDOW PERIMETER- For fillet beads, or angle beads around windows and doors, the sealant should exhibit a minimum surface contact area [C] of 1/4" onto each substrate, with provisions for release at the heel of the angle using backer rod or bond breaker tape.

Cure Time

At 72 °F (22 °C) Dymeric 240FC will reach full cure in about 48 hr. As the temperatures decrease, the cure time will increase. A good rule of thumb is an additional 24 hr for every 10 °F decrease in temperature.

Clean Up

Excess sealant and smears adjacent to the joint interface can be carefully removed with xylene or mineral spirits before the sealant cures. Any utensils used for tooling can also be cleaned with xylene or mineral spirits.

Warranty

Tremco warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL VALUES
Type		Two component gun-grade urethane sealant
Color		Dymeric 240FC is available as a base and curative that can be tinted to your choice of 70 standard colors, or we can match a special color for you. A color pak is not required for the pretint version.
Solids		99%
Specific Gravity		1.06
Application		Gun-grade sealant, applied with typical caulking equipment
Low Temp. Flexibility	ASTM C793	Passes at -15F (-9C)
Hardness, durometer scale "A"	ASTM C661	30 ±3
Weight Loss	ASTM C1246	Passes
Skin Time	ASTM C679	3 hr
Tack Free Time	73.4°F (23°C) 50% RH	19 hr
Stain and Color Change	ASTM C510	No stain, No color change
Adhesion-in-Peel	ASTM C794	>10 pli (pass)
Accelerated Weathering	ASTM C793	Pass
Movement Capability	ASTM C719*	±50%

*Modified

0819/DYMERIC240FCDS-ST

Tremco Commercial Sealants & Waterproofing

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555

