

SpEC Bitmul R HD

RUBBERIZED BITUMEN EMULSION PROTECTIVE COATING

DESCRIPTION

SpEC Bitmul R HD is a rubberized bitumen emulsion supplied as a brown liquid which dries to form a black, flexible coating.

TYPICAL USES

SpEC Bitmul R HD is used where a cold applied, flexible and seamless waterproofing membrane is needed, such as:

- Shallow concrete and brick foundations
- Facades where a vapour / salt barrier behind cladding or curtain walls is required.
- Steel works, pipes and other buried elements

ADVANTAGES

- Excellent adhesion to most building substrates
- Resistant to chlorides, sulphates and other ground and airborne salts
- Efficient curing membrane to newly placed concrete
- Non-hazardous
- Cost-effective

TECHNICAL DATA

Colour	Dark Brown
Specific Gravity	1.00
Polymer content	10%
Solids content	35%
Drying Time	3 hours @ 35 °C
Intercoat time	6 hours @ 35 °C

APPLICATION

Surface Preparation

Surfaces onto which the coating is to be applied must be sound and clean. Dust, loose materials and protrusions must be removed and cracks, holes, etc., made good.

SpEC Bitmul R HD may be applied to damp surfaces such as green concrete providing there is no standing water. Very hot surfaces must be dampened with clean cold water to facilitate application.

Application

The drums must be well stirred before use. Where a single drum is used for prolonged periods, occasional stirring during application is recommended. Apply evenly and in one direction using a stiff brush. A two-coat application is recommended to avoid possible holidays in the film. Each coat must be allowed to dry before applying next one. Do not apply **SpEC Bitmul R HD** to external areas in wet weather or when rain is expected.

EQUIPMENT CLEANING

SpEC Bitmul R HD may be removed from tools and equipment with water when wet. On drying, **SpEC Bitmul R HD** may be removed with **SpECTite Cleaning Fluid**, white spirit or kerosene.

APPLICATION TEMPERATURE RANGE

5 °C to 45 °C

PACKAGING & YIELD

SpEC Bitmul R HD is supplied in 20 litre pails and 200 litre drums with a coverage rate of 1 to 3m²/litre per coat, depending on the porosity of the surface.

STORAGE & SHELF LIFE

Store **SpEC Bitmul R HD** in sealed containers under shade, between 5 °C and 45 °C. Reseal partly used containers tightly after each use. **SpEC Bitmul R HD** has a shelf life of 12 months when stored under favorable conditions.

HEALTH & SAFETY

Skin contact Use gloves or barrier creams when using the material. Clean hands and skin using hand cleaners, followed by washing with soap and water. Do not use solvents.

Eye contact Wash with copious amounts of clean water and seek immediate medical treatment.

Ingestion Do not induce vomiting. Give copious amounts of water to drink and seek immediate medical advice.

Spillage Check the containers periodically for signs of leakage. Recent and discard damaged drums. Spilled materials must be removed immediately using an inert, absorbent medium such as sand, and discarded in a safe place

FLAMMABILITY

SpEC Bitmul R HD is non-flammable, **SpECTite Cleaning Fluid** is flammable. Keep away from open fire, sparks and other ignition sources.

FLASH POINT

SpECTite Cleaning Fluid 34 °C

Issue 1: 03/2014

QA-054

Whilst the information and/or specifications given are, to the best of our knowledge, true and accurate, no warranty is given or implied in any connection with any recommendations or suggestions made by us, our representatives, agents or distributors as the conditions of use and labour involved are beyond our control.

SPECIALITY ENGINEERING CHEMICALS

PO Box 61347, Dubai, United Arab Emirates. Telephone: +971 4 883 6662, Fax: +971 4 883 7696

E-mail: specdxb1@emirates.net.ae

www.spec.ws

Distributed by: **EMIRATES SPECIALITIES CO., L.L.C.**

P.O. Box 3880, Dubai, United Arab Emirates.

Al-Quoz Distribution Centre.

Tel: +971 4 3470767, Fax: +971 4 3470765

E-mail: dubai@esco.ae

P.O. Box 46564, Abu Dhabi, United Arab Emirates.

Tel: +971 2 6784800, Fax: +971 2 6778366

Email: abudhabi@esco.ae

P.O. Box 6156, Sharjah, United Arab Emirates

Tel: +971 6 5420220, Fax: +971 6 5421211

Email: sharjah@esco.ae

“Printed on Recycled Paper”