

SpEC Bitprufe 1000

HIGH BUILD POLYMER MODIFIED ELASTOMERIC BITUMEN MEMBRANE

DESCRIPTION

SpEC Bitprufe 1000 is a liquid applied, high performance bituminous solution modified with synthetic polymers, which when applied dries to form a tough, elastomeric membrane.

TYPICAL USES

SpEC Bitprufe 1000 is used where a tough, flexible and seamless waterproofing membrane is needed, such as:

- Waterproofing and protection of concrete structures above and below ground in buildings and civil engineering works
- Floors of bathrooms, kitchens and other wet areas where multiple pipe entries may render the use of sheet membranes difficult
- Facades where a vapour/salt barrier behind cladding or curtain walls is required
- Flat and pitched roofs, balconies, terraces, etc.
- Recoating old and porous bituminous roof surfaces

ADVANTAGES

- Excellent adhesion to most building substrates
- High build - provides 1.5mm to 2mm DFT in 2 coats
- Bridges non-structural cracks.
- Efficient curing membrane to newly placed concrete
- Excellent temperature resistance - suitable for hot climates

RELEVANT STANDARDS

SpEC Bitprufe 1000 conforms to the following standards:

- BS 8102 Protection of structures against water from the ground
- BS 3690 Bitumens for building and civil engineering
- ASTM D1227
- ASTM D2939

TECHNICAL DATA

Colour	Dark brown, dries to black
Drying time	2 - 3 hours @ 35 °C
Full cure	24 - 48 hours
Service Temperature	0 - 60 °C
Elongation (ASTM D412)	1000%
Solids content (ASTM D2369)	65%
Rubber Content	15±2%

*All values are subject to 5-10% tolerance

APPLICATION

Surface Preparation

Surfaces onto which the membrane is to be applied must be sound and clean. Dust, loose materials and protrusions must be removed and cracks, holes, etc made good.

Porous substrates should be pre-wetted with clean water (remove standing water).

Priming

For maximum adhesion on vertical application and to metal substrates, use one coat of **SpEC Black Bitumen Paint** as a primer at the rate of 5 m²/litre and allow to dry before coating with **SpEC Bitprufe 1000**.

Application

The drums must be well stirred before use. Where a single drum is used for prolonged periods, occasional stirring during application is recommended.

Waterproofing and Wet Areas:

Apply 2 coats of **SpEC Bitprufe 1000** by brush or roller each at 1.25 lit/m² to achieve a 1.5mm DFT, allowing 24-48 hours between coats. On floors continue the application up the walls to a minimum height of 150 mm or link with the damp proof course.

Where **SpEC Bitprufe 1000** is overlaid with screed or tiling adhesive, blind the final coat with clean sharp sand passing a 3 mm sieve to provide a good key.

Vapour/Salt Barrier:

Apply 2 coats of **SpEC Bitprufe 1000** by brush or roller each at 1 litre/m² to achieve a 1.2mm DFT, allowing 24-48 hours between coats. On masonry, all joints must be finished flush and the first coat should fill all the surface pores.

Roof Coating:

Apply 2 coats of **SpEC Bitprufe 1000** by brush or roller each at 1.25 litre/m² coat to achieve a 1.5 mm DFT, allowing 24-48 hours between coats. When used over old sheet membranes, reinforce the membrane overlaps with a 300 mm wide strip of glass cloth between first and second coats. Bed the fibre glass cloth into the first coat while still wet and overcoat with the second after drying.

Protection:

On exterior surfaces applied coatings must be protected from prolonged exposure by **SpECTite Protection Boards** or the subsequent finishes. On floors care should be taken not to damage the coating while laying the protective screed or the tile adhesive. Exposed roof coatings must receive a compatible reflective paint.

EQUIPMENT CLEANING

SpEC Bitprufe 1000 may be removed from tools and equipment with water when wet. On drying, use of **SpECTite Cleaning Fluid**, white spirit or kerosene is recommended.

APPLICATION TEMPERATURE RANGE

5°C to 40°C.

PACKAGING AND YIELD

SpEC Bitprufe 1000 is supplied in 20 litre pails and 200 litre drums. For coverage rates refer to APPLICATION paragraph above.

STORAGE AND SHELF LIFE

Store **SpEC Bitprufe 1000** in sealed containers under shade, between 5°C and 40°C. Reseal partly used containers tightly after each use. When stored

for extended periods, the containers must be rolled periodically to reduce the risk of settlement. **SpEC Bitprufe 1000** has a shelf life of 12 months when stored under favourable conditions.

HEALTH AND SAFETY

Skin Contact

Use gloves or barrier creams when using the material. Clean hands and skin using hand cleaners, followed by washing with soap and water. Do not use solvents.

Eye Contact

Wash with copious amounts of clean water and seek immediate medical treatment.

Ingestion

Do not induce vomiting. Give copious amounts of water to drink and seek immediate medical advice.

Spillage

Check the containers periodically for signs of leakage. Recant and discard damaged drums. Spilled material must be removed immediately using an inert, absorbent medium such as sand, and discarded in a safe place.

FLAMMABILITY

SpEC Bitprufe 1000: Non-flammable. **SpECTite**

Cleaning Fluid: Flammable; Keep away from open fire, sparks and other ignition sources.

FLASH POINT

SpECTite Cleaning Fluid 34 ° C

SpEC Black Bitumen Paint 32 ° C

See separate data sheets for ancillary items:

- **SpEC Black Bitumen Paint**
- **SpECTite Protection Boards**

Issue 5: 01/2023

QA-054

Whilst the information and/or specifications given are, to the best of our knowledge, true and accurate, no warranty is given or implied in any connection with any recommendations or suggestions made by us, our representatives, agents or distributors as the conditions of use and labour involved are beyond our control.

If it is proven that the product does not perform as described in our TDS, SpEC's liability extends solely to the free replacement of product, once the claim has been accepted after due investigation by SpEC. SpEC will not entertain any claims involving any form of consequential costs or damages such as shipping costs, custom duties, damages to third parties, damages to structures, penalties from delay of a project or any other form of consequential damage.

SPECIALITY ENGINEERING CHEMICALS

PO Box 61347, Dubai, United Arab Emirates. Telephone: +971 4 883 6662, Fax: +971 4 883 7696

E-mail: info@spec.ae

www.spec.ws

Distributed by: EMIRATES SPECIALITIES CO., LLC

P.O. Box 3880, Dubai, United Arab Emirates.

Al-Quoz Distribution Centre.

Tel: +971 4 3470767, Fax: +971 4 3470765

E-mail: dubai@esco.ae

P.O. Box 46564, Abu Dhabi, United Arab Emirates.

Tel: +971 2 6784800, Fax: +971 2 6778366

Email: abudhabi@esco.ae

P.O. Box 6156, Sharjah, United Arab Emirates

Tel: +971 6 5420220, Fax: +971 6 5421211

Email: sharjah@esco.ae

"Printed on Recycled Paper"